



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : C09B 67/22, D06P 3/42, C09B 29/045	A1	(11) International Publication Number: WO 00/43454 (43) International Publication Date: 27 July 2000 (27.07.00)
(21) International Application Number: PCT/GB00/00119 (22) International Filing Date: 20 January 2000 (20.01.00) (30) Priority Data: 9901303.9 22 January 1999 (22.01.99) GB (71) Applicant (for all designated States except US): YORKSHIRE CHEMICALS PLC [GB/GB]; Kirkstall Road, Leeds LS3 1LL (GB). (72) Inventors; and (75) Inventors/Applicants (for US only): WHITHAM, Christopher [GB/GB]; 22 Round Hill, Darton, Barnsley, South Yorkshire S75 5QJ (GB). BUCKLEY, Alan, John [GB/GB]; 14 Brookway, Grasscroft, Oldham OL4 4EU (GB). CROWSON, Rebecca, Jane [GB/GB]; 49 Lumley Road, Burley, Leeds LS4 2NH (GB). (74) Agent: W.P. THOMPSON & CO.; Coopers Building, Church Street, Liverpool L1 3AB (GB).		(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>
(54) Title: DYE COMPOSITION <div style="text-align: center;"> </div> <div style="text-align: right;">(II)</div> <div style="text-align: center;"> </div> <div style="text-align: right;">(III)</div> (57) Abstract <p>The invention provides a dye composition for dyeing fibres comprising (a) an azo dye of formula (II) or a salt thereof, and (b) an azo dye of formula (III) or a salt thereof. The invention provides navy and black dye compositions, especially suitable for dyeing secondary cellulose acetate fibres, with superior fastness properties than known navy/black dyes. Preferably, the α-crystal form of dye (III) is used, which has greater solubility and achieves quicker dyeing than the commonly-used β and γ forms of (III) when dyeing cellulose acetate at 60–95 °C. A new method of making the α form is disclosed.</p>		

BEST AVAILABLE COPY

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.


AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

DYE COMPOSITION

The present invention relates to novel dye compositions for dyeing cellulose acetate fibres, especially secondary acetate fibres and blends of secondary acetate fibres with other fibres both natural and synthetic.

Mixtures of disperse dyes are well known for the dyeing of synthetic fibres, particularly for polyester and for secondary cellulose acetate fibres and their blends with other fibres.

Polyester fibres in particular are well served both in the inventive art of, and in the commercial availability of, disperse dye mixtures which provide navy and black shades with good application properties and good fastness to washing and to light. Many such mixtures are based upon the mixture of two or more dyes of general structure (I), where X may be hydrogen or alkoxy, and R and R' may be alkyl or alkenyl. Such mixtures are exemplified in, for example US 5,393,308 (to BASF) and GB 1,582,743 (to ICI), and commercially provide economic navy and black shades of adequate fastness when applied to polyester.



These mixtures, and many other mixtures which are based upon high energy dyes, are however unsuitable for the dyeing of secondary cellulose acetate.

- 2 -

It is an object of the present invention to provide novel disperse dye mixtures, based upon known dyes, which are especially suitable for the dyeing of secondary cellulose acetate.

Secondary cellulose acetate fibres are commonly used as linings on coats and suits. Dyeing of the fibres usually takes place at less than 100°C at atmospheric pressure in water. The main commercial acetate fibre dyes are black. However, very few companies offer good black dyes for acetate fibres.

Dyes of formula (II) and (III), as identified hereafter, are previously known dyes for the dyeing of synthetic fibres. The preparation of dye (II), and the use of the dye in the coloration of aromatic polyester textile materials is exemplified in example 1 of UK patent 1,394,367 (ICI). Commercial preparations of the dye are available and recommended for use on polyester fibres as Dispersol Blue XF (trade mark BASF) and Serilene Blue HWF (trade mark Yorkshire Chemicals). However, dye (II) has never to the applicant's knowledge been used on acetate fibres before.

Dye (III) is disclosed in Claim 5 and page 10 of UK Patent 1,112,146 (BASF) and is commercially available and recommended for use on polyester fibres as Palanil Dark Blue 3RT (trade mark BASF) and Serilene Dark Blue RT-LS (trade mark Yorkshire Chemicals). Two new (β - and γ -) crystal forms of dye (III) are disclosed in UK patent 1,438,586 (BASF).


No previous use of the dyes (II) and (III) in admixture for the coloration of textiles has been found, and there is no suggestion in the prior art that (II) and (III)

- 3 -

should be combined.


According to a first aspect of the present invention there is provided a dye composition for dyeing fibres comprising

(a) an azo dye of the formula (II):



or a salt thereof, and

(b) an azo dye of the formula (III):



or a salt thereof.

When referring to dyes (II) and (III) throughout the specification, the salts thereof are intended to be included. The same applies for dyes (IV) to (IX) defined hereinafter.

SUBSTITUTE SHEET (RULE 26)

- 4 -

The dye composition of the present invention is blue, and can form the basis of navy and black dye compositions for providing navy or black shades on, for example, secondary cellulose acetate fibres.

The dye composition is especially suitable for dyeing secondary cellulose acetate fibres. From the resultant dyeings, it has been found that the dye compositions of the present invention display fastness properties superior to those provided by dye compositions currently available for the provision of navy and black shades on secondary cellulose acetate. This superior fastness extends to blends of secondary cellulose acetate with other fibres, for instance with wool, viscose fibres and synthetic elastomeric fibres.

The exact shade achieved by the blue mixture or composition of the present invention may be changed by varying the proportions of the two dyes, and may be varied further by the addition of one or more further blue dyes to the dye composition.

Preferably, the dye composition comprises from 20% to 80% of dye (II) and from 20% to 80% of dye (III), by weight of the total amount of dyes (II) and (III) in the composition.

The BASF inventors of UK patent 1,438,586 claim that the β - and γ -forms or modifications of the dye (III) disclosed therein have better stability under liquor dyeing conditions (100-200°C, eg. up to 140°C) and better rheological properties than the α -form (crystal form) or α -modification of dye (III), which

- 5 -

was previously known for dyeing of polyester and cellulose acetate. However, the present inventor has now found that, contrary to the indications in GB 1,438,586, the α - form is actually superior for dyeing cellulose acetate (eg. secondary acetate) fibres giving a better rate of dyeing than the β - and γ forms of dye (III), so that a shorter time is required in the dye bath, and producing a more on-tone build up of the required navy or black shade on the fibres. Without being bound by theory, this quicker dyeing is thought to be because the α - form of dye (III) has a greater solubility than the β - and γ - forms in the dye bath at typical acetate dyeing temperatures of about 75 - 85°C. This increased solubility in turn is probably because the α - form of (III) is less thermodynamically stable and has a lower melting point and crystal energy than the β - and γ - forms.

The α - form of dye (III) has an X-ray diffraction graph (CuK α radiation) having a characteristic line of strong intensity at a diffraction angle 2θ of 25.5°, and lines of medium intensity at diffraction angles of 5.9°, 12.1°, 13°, 14.2°, 15.9°, 17.8°, 18.4°, 24.1°, 26° and 28°.

Therefore, in a particularly preferred embodiment of the present invention, some or all of the dye (III) is present in an α - form characterised substantially by the above X-ray diffraction graph. Preferably $\geq 50\%$, more preferably $\geq 80\%$, even more preferably $\geq 95\%$ and most preferably 100% of the dye (III) is present in the α - form.

Alternatively, the dye (III) can comprise or can be present in, or some or all of the dye (III) can be present in, the β -form and/or the γ -form of dye (III).



- 6 -

The β - and γ -crystal forms of dye (III) are disclosed in UK patent 1,438,586, and are characterised substantially by x-ray diffraction graphs (CuK_α radiation) as follows:

β -form: line of strong intensity at a diffraction angle 2θ [°] of 25.3; lines of medium intensity at diffraction angles 2θ [°] of 7.3, 13.6, 13.9, 16.7, 21.1, 23.1 and 29.0; and optionally lines of weak intensity at diffraction angles 2θ [°] of 14.3, 18.3, 19.8, 22.6 and 26.1. γ -form: line of strong intensity at a diffraction angle 2θ [°] of 24.5; lines of medium intensity at diffraction angles 2θ [°] of 10.9, 18.3 and 22.3; and optionally lines of weak intensity at diffraction angles 2θ [°] of 9.0, 17.8, 20.8, 23.2, 26.2, 27.6 and 28.0.

- 7 -

Optionally, the dye composition additionally comprises an azo dye of the formula (VI) and/or an azo dye of the formula (IX):



or one or more salts thereof.

The dyes (VI) and (IX) are also blue and further vary the shade achieved by a basic blue composition containing dyes (II), (III) and [(VI) and/or (IX)] and no other dyes.

Preferably, the dye composition comprises from 20% to 70%, or more preferably from 30% to 60%, of dye (VI) or of dye (IX) or of the total weight of dyes (VI) and (IX), by weight of the total weight of dye (II) and dye (III) in the composition.





Other blue dyes may also be used in addition to or instead of dyes (VI) and (IX), and may be present in the same proportions as those preferred for (VI) and/or

SUBSTITUTE SHEET (RULE 26)

(IX).

Preferably, the dye composition comprises one or more additional dyes (preferably azo dyes) adapted to give the dye composition and/or fibres with which the composition comes into contact a black shade. These dyes can include (i) yellow dyes, (ii) yellow-brown or brown dyes, (iii) orange dyes and/or (iv) red dyes, these dyes preferably being suitable for dyeing acetate. These additional dyes can be added to the composition of the invention in a manner familiar to those skilled in the art to convert the blue dye mixture into black mixtures which have superior properties for the dyeing of cellulose acetate fibres (e.g. secondary cellulose acetate fibres). Obviously, the exact tone of the black dye mixture derived, when dyed on cellulose acetate fibres, will depend upon the type, and proportions of the further dyes added.

More preferably, the one or more additional dyes can include the orange dye of formula (IV), the brown dye of formula (V), the red dye of formula (VII) and/or the yellow dye of formula (VIII), and/or a salt or salts thereof.



The general principle of producing a black effect by colour mixture is well known, and is described in such texts as "Color - An Introduction to Practice and Principles", author R.G. Kuehni, [John Wiley & Sons Inc., 1997]. The application of this principle to dyestuffs mixtures is also well known, and is exemplified in the previously referenced US 5,393,308 (BASF).

The dye composition preferably contains from 10 to 50% of dyes by weight of the total weight of the dry ingredients of the composition, and/or additionally contains from 50 to 90% of a dispersant or a plurality of dispersants by weight of the dry ingredients of the composition. The dye composition may be required either as a solid or a liquid. The composition may thus contain between 0 and 90wt% water. A lignin sulphonate may be used as a dispersant.

- 10 -

The novel dye compositions may also contain other non-dye components which, typically, enhance the dyeing properties of the dye compositions in the dyeing process. These components include, for example, lignin sulphonates and the products of sulphonation or sulphomethylation of the condensates of formaldehyde with aromatic compounds.

The essential components of the dye composition of the present invention can be prepared and/or obtained commercially as follows. Dyes (II) and (III) are previously known dyes for the dyeing of synthetic fibres. The dye (II) can be prepared by the method exemplified in example 1 of UK patent 1,394,367 (ICI). Commercial preparations of dye (II) are also available and recommended for use on polyester fibres as Dispersol Blue XF (trade mark BASF) and Serilene Blue HWF (trade mark Yorkshire Chemicals plc, Kirstall Road, Leeds, LS3 1LL, United Kingdom). Dye (III) is disclosed in claim 5 and page 10 of UK patent 1,112,146 (BASF) and is commercially available and recommended for use on polyester fibres as Palanil Dark Blue 3RT (trade mark BASF) and Serilene Dark Blue RT-LS (trade mark Yorkshire Chemicals). A prior art synthesis of the α -form of the dye (III) is suggested in German patent No. 1,544,375; and a new improved synthesis is disclosed hereinafter.

The dye compositions may be prepared using conventional methods whereby the individual component dyes may be separately processed with the dispersing agent or agents, followed by the blending of the individually finished dyes in the required ratios. Alternatively, the dyes may be combined in the

- 11 -

required proportions prior to processing (e.g. by adding the dispersing agent or agents).

According to a second aspect of the present invention, therefore, there is provided a method of making a dye composition according to the present invention, comprising mixing the dyes together, preferably in the stated weight ratios.

According to a third aspect of the present invention, there is provided a dye bath composition comprising a dye composition according to the present invention and water. Usually, the dye composition is dispersed in the water.

According to a fourth aspect of the present invention, there is provided a method of dyeing fibres comprising contacting fibres with a dye composition or dye bath composition of the present invention in a dye bath.

Preferably, the fibres comprise cellulose acetate fibres (more preferably secondary cellulose acetate fibres) or blends thereof with other natural and/or synthetic fibres such as wool, viscose, and/or synthetic elastomeric fibres.

Preferably, the dye bath is brought to a raised temperature after the fibres have been introduced into the dye bath. Preferably, after the fibres have been introduced into the dye bath, the dye bath is gradually heated to 60-95°C, more preferably to about 75-90°C, even more preferably to about 85°C. In commercial operation the actual dyeing takes place in the jig or jet dyeing machine or the like when the fabric is only wetted with the dye liquor and the actual dyeing probably takes place at a temperature of about 10°C less than that of the dye bath.

Preferably, the fibres are left in the hot dye bath or machine until dyeing

- 12 -

is substantially complete. This may take from one to eight hours depending upon the temperature and the type of machine used. The dye bath is then preferably gradually cooled (usually to 40-70°C) before removing the fibres, and preferably the fibres are then rinsed. The method is suitable for dyeing fibres in the form of textile fabrics.

The method of dyeing may also comprise later steps (after removing the fibres from the dye bath) of reduction clearing the fibre, rinsing the fibre, drying the fibre, and/or stentering the fibre.

According to a fifth aspect of the present invention there are provided fibres and/or a textile material dyed using a dye composition, dye bath composition and/or method of the present invention. Preferably, the fibres and/or textile material comprise cellulose acetate fibres (more preferably secondary cellulose acetate fibres) or blends thereof with other natural and/or synthetic fibres such as wool, viscose and/or synthetic elastomeric fibres.

According to a sixth aspect of the present invention, there is provided a method of making an α -form of the dye (III) or a salt thereof as defined above, comprising the steps of:-

(a) reacting 3-amino-5-nitro-2,1-benzisothiazole or a salt thereof with a diazotising agent, and

(b) coupling the diazotised benzothiazole with N-ethyl-N-[2-(methoxycarbonyl)ethyl]aniline or a salt thereof.

Preferably, the diazotising agent comprises nitrosyl sulfuric acid (e.g. formed in situ from sodium nitrite in sulfuric acid)

- 13 -

Preferably step (a) is carried out in a solvent which comprises sulfuric acid (e.g. $\geq 90\%$ e.g. 95-99% sulfuric acid by weight of water present), and/or at a temperature of -20 to 5°C , more preferably 0 to 5°C . The preferred duration of step (a) is 3 to 4 hours.

Preferably, step (b) is carried out in aqueous medium.

Preferably, in step (b) the diazotised benzothiazole is added gradually (e.g. continually or batchwise) to a reaction vessel containing the N-ethyl-N-[2-(methoxy carbonyl)ethyl] aniline or the salt thereof. Preferably, the temperature is maintained at -10°C to 10°C , more preferably -5°C to 0°C , during the gradual addition. The pH is preferably substantially maintained at 3-6, more preferably 4-5, during the gradual addition (e.g. by addition of base or alkali). After the gradual addition, the reaction mixture is acidified and preferably heated to $\geq 25^{\circ}\text{C}$. More preferably $\geq 50\%$ for a period of 10 minutes to 3 hours., more preferably for 60 to 90 minutes.

According to a seventh aspect of the present invention, there is provided a method of making a dye composition according to the first aspect of the invention comprising:

- a) making an α -form of the dye (III) or a salt thereof as defined above according to the sixth aspect of the present invention, and
- b) mixing said α -form of dye (III) or salt thereof with one or more dyes including dye (II) or a salt thereof.

Examples

- 14 -

Specific embodiments of the present invention will now be described, by way of example only. Throughout the examples all parts are parts by weight unless otherwise specified.

Example 1 - basic composition with dyes (II) and (III)

A blue dye composition was prepared comprising 57.9 parts of dye (II) with 42.1 parts of dye (III) and 204 parts of a lignin sulphonate dispersing agent. This composition was used to dye a secondary cellulose acetate fabric at 1/1 and 2/1 depths by applying 0.7wt% and 1.4wt% of the dye composition by weight of fibre using the following method. The depths of dyeing are defined in British Standard BS2661:SDG:1961 issued by the British Standards Institution in collaboration with the Society of Dyers and Colourists (ISO R105/1).

A 4g piece of a standard woven secondary cellulose acetate lining fabric was immersed in 80ml of water containing the dye and 0.8ml Dyapol BDN (trade mark of and available from Yorkshire Chemicals), a dye bath dispersant. The solution was adjusted to pH 4.5 using dilute acetic acid. The liquors and fabric were heated to 85°C at 1.5°C/min, and then maintained at 85°C for an hour. At the end of this period, the dye bath was allowed to cool, and the fabric removed and rinsed with warm water before drying.

The fastnesses of the resultant dyeings were assessed by means of the standard grey scale against Celliton Blue GF (trade mark - BASF) applied to the same depth of shade by the same standard dyeing method. Celliton Blue GF is a blue dye composition which is sold specifically for the dyeing of secondary

- 15 -

cellulose acetate fabrics, it being a market leading dye composition in this category. These tests methods are taken from British Standard BS1006:1990 issued by the British Standard Institution.

CO6 A2S Wash Fastness Test

	1/1 Depth							2/1 Depth						
	CS	CA	Co	Pa	Pes	Pac	Wo	CS	CA	Co	Pa	Pes	Pac	Wo
Example 1	5	4/5	5	4/5	4/5	5	5	5	4	5	4	4	5	5
Celliton Blue GF	5	4	5	4	4/5	5	5	5	3/4	4/5	3/4	4	5	5

In brief, this test involves washing the dyed cellulose acetate fabric at 40°C in the presence of a test fabric comprising strips of various types of undyed fabric, and observing the degree of transfer of dye from the dyed fabric to the undyed fabrics. In the above table, the numbers represent the cross-staining of the dye from the cellulose acetate textile to test strips of:

CACellulose Acetate

CoCotton

PaNylon 6.6

PesPolyester

PacAcrylic

WoWool

CS stands for change in shade, i.e. a measure of the colour lost by the dyed acetate fabric during the washing test.

In all cases, the staining is assessed on a 1-5 scale where 5 represents no staining and 1 represents severe staining. Therefore, the higher the staining

- 16 -

number, the better the fastness of the dye on the dyed fabric. It is noted that the small numerical differences seen between the Example 1 fabric and the Celliton Blue CF fabric actually represent a significant visual difference in the degree of staining.

CO6 B2S Wash Fastness Test

	1/1 Depth							2/1 Depth						
	CS	CA	Co	Pa	Pes	Pac	Wo	CS	CA	Co	Pa	Pes	Pac	Wo
Example 1	5	4	5	4	4/5	5	5	5	3/4	4/5	3/4	4	5	5
Celliton Blue GF	5	3/4	5	3/4	4	5	5	5	3	4/5	3	4	5	4/5

The CO6 B2S test is the same as the CO6 A2S test but uses a 50°C wash instead of a 40°C wash.

EO1 Cold Water Test

	1/1 Depth							2/1 Depth						
	CS	CA	Co	Pa	Pes	Pac	Wo	CS	CA	Co	Pa	Pes	Pac	Wo
Example 1	5	4/5	5	4/5	5	5	5	5	4	4/5	4	4/5	5	4/5
Celliton Blue GF	5	4/5	4/5	5	4/5	5	5	5	4	4/5	4	4/5	5	4/5

The EO1 cold water test involves wetting the dyed acetate fabric and undyed test fabric with deionised water, placing the wet dyed acetate fabric in contact with wet undyed test fabric, placing a weight on top of the two contacted fabrics, and measuring how much colour is transferred after rinsing.

- 17 -

E04 Alkaline Perspiration Test pH8

	1/1 Depth							2/1 Depth						
	CS	CA	Co	Pa	Pes	Pac	Wo	CS	CA	Co	Pa	Pes	Pac	Wo
Example 1	5	5	5	5	5	5	5	5	4/5	5	4/5	4/5	5	5
Cellinton Blue GF	5	4/5	5	4/5	5	5	5	5	4	4/5	4	4/5	5	4/5

The EO4 test is the same as the above EO1 test except that an aqueous synthetic perspiration of alkaline pH replaces the deionised water of the EO1 test.

G01 Nitrogen Oxides Test

This test measures the resistance of the dye colour on cloth to fading caused by gas fumes. Again, 5 represents the best result, through to 1 which is the worst.

		1 Cycle	3 Cycles
Example 1	1/1 Depth	5	4/5
	2/1 Depth	5	4/5
Celliton Blue GF	1/1 Depth	5	4/5 redder
	2/1 Depth	5	4 redder

Example 2 - Composition with seven dyes including blue dye (VI)

A black dye composition was prepared comprising 12 parts of blue dye (II) and 25.5 parts of blue dye (III) along with the following dyes:-

Orange dye (IV) 24.8 parts

Brown dye (V) 13.33 parts

Blue dye (VI) 14.4 parts

Red dye (VII) 7.25 parts

- 18 -

and Yellow dye (VIII) 2.73 parts

and 170 parts of a lignin sulphonate dispersing agent. This composition was used to dye a secondary cellulose acetate fabric to B/Dk depth by applying 4% by weight of fibre using the same method exemplified in Example 1. The dyeing depth and the fastness testing methods are defined in the same way as in Example 1. The fastness test results are compared with those obtained using three leading commercial black dye compositions for secondary cellulose acetate. Serisol is a trade mark of Yorkshire Chemicals, and Celliton is a trade mark of BASF.

C06 A2S Wash Fastness Test

	CS	CA	Co	Pa	Pes	Pac	Wo
Example 2	5	3/4	4/5	3/4	4	4/5	4/5
Serisol Black BSNX03 Liquid 50	5	3/4	4/5	3	4	4/5	4/5
Serisol Black BSN	5	3/4	4/5	3	4	4/5	4/5
Celliton Black GFG	5	3/4	4/5	3	4	4/5	4/5

EO1 Cold Water Test

	CS	CA	Co	Pa	Pes	Pac	Wo
Example 2	5	4	4	4	4	4/5	4/5
Serisol Black BSNX03 Liquid 50	5	4	4	4	4	4/5	4/5
Serisol Black BSN	5	3/4	4	3/4	4	4/5	4/5
Celliton Black GFG	5	4	4	4	4	4/5	4/5

- 19 -

EO4 Alkaline Perspiration Test pH8

	CS	CA	Co	Pa	Pes	Pac	Wo
Example 2	5	4	4	4	4	4/5	4/5
Serisol Black BSNX03 Liquid 50	5	4	4	4	4	4/5	4/5
Serisol Black BSN	5	3/4	4	3/4	4	4/5	4/5
Celliton Black GFG	5	4	4	4	4	4/5	4/5

G01 Nitrogen Oxides Test

	1 Cycle	3 Cycles
Example 2	4	3/4
Serisol Black BSNX03 Liquid 50	4	3/4
Serisol Black BSN	4/5	4
Celliton Black GFG	4	3/4

Light Fastness (Xenotest BO2)Blue Scale Rating

Example 2	5
Serisol Black BSNX03 Liquid 50	4
Serisol Black BSN	4
Celliton Black GFG	4/5

The light fastness test is an accelerated weathering test using a xenon lamp (white light) to simulate daylight and the fading of the dye colour caused by daylight. The higher the Blue Scale Rating, the lower the degree of fading.

- 20 -

Example 3 - Composition with seven dyes including blue dye (IX).

A black dye composition was prepared comprising 11.7 parts of blue dye (II) and 23.5 parts of blue dye (III) along with the following dyes:-

Orange dye (IV) 23.2 parts

Brown dye (V) 12.3 parts

Blue dye (IX) 19.8 parts

Red dye (VII) 7 parts

and Yellow dye (VIII) 2.5 parts

and 170 parts of a lignin sulphonate dispersing agent. The composition was used to dye a secondary cellulose acetate fabric to B/Dk depth by applying 4% by weight of fibre using the same method exemplified in Example 1. The dyeing depth and the fastness testing methods are defined in the same way as in Example 1. The fastness test results are compared with those obtained using three leading commercial black dye compositions for secondary cellulose acetate. Serisol is a trade mark of Yorkshire Chemicals, and Celliton is a trade mark of BASF.

CO6 A2S Wash Fastness Test

	CS	CA	Co	Pa	Pes	Pac	Wo
Example 3	5	4	5	4	4/5	5	5
Serisol Black BSNX03 Liquid 50	5	3/4	4/5	3	4	4/5	4/5
Serisol Black BSN	5	3/4	4/5	3	4	4/5	4/5
Celliton Black GFG	5	3/4	4/5	3	4	4/5	4/5

- 21 -

EO1 Cold Water Test

	CS	CA	Co	Pa	Pes	Pac	Wo
Example 3	5	4	4/5	4	4/5	5	5
Serisol Black BSNX03 Liquid 50	5	4	4	4	4	4/5	4/5
Serisol Black BSN	5	3	4/5	3/4	4	4/5	4/5
Celliton Black GFG	5	4	4	4	4	4/5	4/5

EO4 Alkaline Perspiration Test pH8

	CS	CA	Co	Pa	Pes	Pac	Wo
Example 3	5	4/5	5	4	5	5	5
Serisol Black BSNX03 Liquid 50	5	4	4	4	4	4/5	4/5
Serisol Black BSN	5	3/4	4	3/4	4	4/5	4/5
Celliton Black GFG	5	4	4	4	4	4/5	4/5

The light fastness test is an accelerated weathering test using a xenon lamp (white light) to simulate daylight and the fading of the dye colour caused by daylight. The higher the Blue Scale Rating, the lower the degree of fading.

GO1 Nitrogen Oxides Test

	1 Cycle	3 Cycles
Example 3	5	5
Serisol Black BSNX03 Liquid 50	4	3/4
Serisol Black BSN	4/5	4
Celliton Black GFG	4	3/4

Example 4 - Synthesis of α -form of dye (III)

The preferred α -form of dye (III) is prepared in the following manner.

3-Amino-5-nitro-2,1-benzisothiazole (19.5 parts) are dissolved in 98% sulphuric acid (97.9 parts).

A solution of nitrosyl sulphuric acid is then prepared as follows:- 7.7 parts of the sodium nitrite is added incrementally to 67.3 parts of 98% sulphuric acid at 20-30°C. The mixture is then heated and maintained at 70°C until reaction is complete (approximately 20 minutes) before cooling the reaction mixture to 30°C.

The benzthiazole solution is cooled to 5°C and the nitrosyl solution added maintaining the temperature at 0-5°C. Glacial acetic acid (24.4 parts) is then added portionwise to the above mixture, again maintaining the 0-5°C temperature regime. The total mixture is then stirred at the same temperature for 5 hours to allow the diazotisation reaction to proceed to completion.

The coupling bath is prepared as follows:-

Water (400 parts), sulphamic acid (2 parts), sodium acetate (50 parts), N-ethyl-N-[2-(methoxycarbonyl)ethyl]aniline (20.7 parts) and an ammonium salt of a sulphonated lignin (2.5 parts) are combined and stirred to produce a fine suspension of pH 5-6. This suspension is then cooled by the addition of ice (600 parts) to <0°C, before the diazo solution prepared above is added as in the following manner.

The diazotised benzothiazole solution is then added to the coupling bath

- 23 -

over a period of 30 minutes maintaining the coupling bath at a pH of 4-5 using additions of 50% caustic soda solution as required. During the addition, the temperature is maintained at $<0^{\circ}\text{C}$. After stirring for 30 minutes the pH of the coupling liquor is reduced to 2-2.5, by the addition of 36% hydrochloric acid, and the resultant azo dye slurry diluted to twice the volume with water. The diluted slurry is heated to 75°C maintaining the pH at 2-2.5 by the addition of further 36% hydrochloric acid as needed. After 2 hours at this temperature, the dye solid is isolated by filtration. This procedure typically yields 81 parts of a water-wet paste (45% solids) of the α -modification of dye (III). The absence of β - and γ -modifications may be confirmed by X-ray crystallography or by the determination of the melting point by DSC.

Example 5 - Comparative tests of α -, β - and γ - forms of dye (III)

Cellulose diacetate cloth is conventionally dyed by Jig dyeing. In such an apparatus, where dyeing takes place typically at $75\text{-}85^{\circ}\text{C}$, the rate of transfer of the disperse dye to the cloth may be much lower than that experienced in the dyeing of polyester which is typically carried out at 130°C . The temperature sensitivity of a disperse dye preparation made from the α - form of dye (III) was compared with that of two commercially available dye preparations of (III) Palanil Dark Blue 3RT and Celliton Blue CA (both registered trade marks of and available from BASF), which are both composed of mixed β - and γ - forms of dye (III).

4g pieces of a standard cellulose diacetate cloth were placed in 200ml containers with the various dye preparations in quantities sufficient to provide a

- 24 -

dyeing of 1/1 depth at full exhaustion. Depths of dyeing are defined in British Standard BS2661:SDG:1961 issued by the British Standards Institution in collaboration with the Society of Dyers and Colourists (ISO R105/1). To the cloth and the dye was added 80ml water and 1ml/1 Dyapol BDN (Registered Trade Mark of and available from Yorkshire Chemicals), a dyebath dispersant. The pH of the mixture was adjusted to 4.5 using acetic acid, before the containers were sealed and heated in a Mathis Labomat infra-red dyeing machine for the following different times and temperatures:-

1 hour at 65°C

2 hours at 65°C

1 hour at 75°C

2 hours at 75°C

1 hour at 85°C

The dye containers were cooled to ambient temperature, opened, and the cellulose diacetate cloth pieces rinsed and dried, before the relative Integ values were determined by reflection. (The definition and measurement of Integ values is discussed in the paper: Value Analysis of Dyes - A New Method Based on Colour Measurement - Journal of the Society of Dyers and Colourists 96 p166-176, April 1980, by A.N. Derbyshire and W.J. Marshall) The relative Integ values are displayed below.

<u>Temp/Time</u>	<u>Palanil Dark Blue 3RT</u>	<u>Celliton Blue CA</u>	<u>α-form (III)</u>
------------------	------------------------------	-------------------------	---------------------------------------

- 25 -

1 hour/65°C	34	34	76
2 hours/65°C	52	48	96
1 hour/75°C	78	79	99
2 hours/75°C	89	90	100
1 hour/85°C	100	100	100


It is obvious from the Integ measurements that the dye preparation containing the α -form of dye (III) gives a more rapid build-up at the temperatures typical for the dyeing of acetate fibres and fabrics. Employment of the α -form of dye (III) for mixtures providing navy and black shades on cellulose triacetate gives faster build-up of colour which is more on tone than if the β - or γ - forms or mixtures of the different forms is employed. Machine productivity and robustness of the dyeing method are thus enhanced by the use of the α -form of dye (III).

- 26 -

CLAIMS


1. A dye composition for dyeing fibres comprising

(a) an azo dye of the formula (II):



or a salt thereof, and

(b) an azo dye of the formula (III):



or a salt thereof.

2. A dye composition as claimed in claim 1, wherein the dye composition comprises from 20% to 80% of dye (II) and from 20% to 80% of dye (III), by weight of the total amount of dyes (II) and (III) in the composition.

3. A dye composition as claimed in claim 1 or 2, wherein some or all of the dye (III) is present in an α -form characterised substantially by an X-ray diffraction graph (CuK_α radiation) having a characteristic line of strong intensity

- 27 -

of a diffraction angle 2θ of 25.5° , and lines of medium intensity at diffraction angles of 5.9° , 12.1° , 13° , 14.2° , 15.9° , 17.8° , 18.4° , 24.1° , 26° and 28° .



4. A dye composition as claimed in claim 3, wherein $\geq 50\%$ of the dye (III) is present in the α form.

5. A dye composition as claimed in claim 3, wherein $\geq 95\%$ of the dye (III) is present in the α -form.

6. A dye composition as claimed in claim 1 or 2, wherein the dye (III) comprises the β -form and/or the γ -form of the dye.

7. A dye composition as claimed in claim 1 or 2 or 6, wherein the dye (III) is present in the β -form and/or the γ -form of the dye.

8. A dye composition as claimed in anyone of the preceding claims, wherein the dye composition additionally comprises an azo dye of the formula (VI) and/or an azo dye of the formula (IX):



9. A dye composition as claimed in claim 8, wherein the dye composition comprises from 20% to 70% of dye (VI) or of dye (IX) or of the total weight of





SUBSTITUTE SHEET (RULE 26)

- 28 -

dyes (VI) and (IX), by weight of the total weight of dye (II) and dye (III) in the composition.

10. A dye composition as claimed in any one of the preceding claims, wherein the dye composition comprises one or more additional dyes (preferably azo dyes) adapted to give the dye composition and/or fibres with which the composition comes into contact a black shade.

11. A dye composition as claimed in claim 10, wherein the one or more additional dyes include the orange dye of formula (IV), the brown dye of formula (V), the red dye of formula (VII) and/or the yellow dye of formula (VIII), and/or a salt or salts thereof.



12. A dye composition as claimed in any one of the preceding claims,

- 29 -

wherein the dye composition contains from 10 to 50% of dyes by weight of the total weight of the dry ingredients of the composition, and/or additionally contains from 50 to 90% of a dispersant or a plurality of dispersants by weight of the dry ingredients of the composition.

13. A dye composition as claimed in any one of the preceding claims containing between 0 and 90wt% water.

14. A method of making a dye composition according to any one of claims 1 to 13, comprising mixing the dyes together.

15. A method as claimed in claim 14, wherein the dyes are mixed in the weight ratios stated in claim 2, 4, 5, 9, 12 and/or 13.

16. A dye bath composition comprising a dye composition according to any one of claims 1 to 13 and water.

17. A method of dyeing fibres comprising contacting fibres with a dye composition as defined in any one of claims 1 to 13 or a dye bath composition as defined in claim 16 in a dye bath.

18. A method as claimed in claim 17, wherein after the fibres have been introduced into the dye bath, the dye bath is gradually heated to 60-100°C.

19. A method as claimed in claim 17 or 18, wherein after removing the fibres from the dye bath, the fibres are reduction cleared, rinsed, dried and/or stentered.


20. Fibres and/or a textile material dyed using a dye composition, dye bath composition and/or method of dyeing as defined in any one of claims 1 to 13 or 16

- 30 -

to 19.

21. A method, fibres or a textile material as claimed in any one of claims 17 to 20, wherein the fibres and/or textile material comprise cellulose acetate fibres or blends thereof with other natural and/or synthetic fibres.

22. A method of making an α -form of an azo dye of the formula (III)



or of a salt of the dye, wherein the α -form is characterised substantially by an X-ray diffraction graph (CuK_α radiation) having a characteristic line of strong intensity at a diffraction angle 2θ of 25.5° , and lines of medium intensity at diffraction angles of 5.9° , 12.1° , 13° , 14.2° , 15.9° , 17.8° , 18.4° , 24.1° , 26° and 28° ;

the method comprising the steps of:

- (a) reacting 3-amino-5-nitro-2,1-benzothiazole or a salt thereof with a diazotising agent, and
- (b) coupling the diazotised benzothiazole with N-ethyl-N-[2-(methoxycarbonyl)ethyl]aniline or a salt thereof.

23. A method as claimed in claim 22, wherein the diazotising agent comprises nitrosyl sulfuric acid.

- 31 -

24. A method as claimed in claim 22 or 23, wherein step (a) is carried out in a solvent which comprises sulfuric acid and/or at a temperature of -20 to 5°.

25. A method as claimed in claim 22, 23 or 24 wherein in step (b) the diazotised benzothiazole is added gradually to a reaction vessel containing the N-ethyl-N-[2-(methoxycarbonyl)ethyl] aniline or the salt thereof.

26. A method as claimed in claim 25, wherein the temperature is maintained at $\leq 0^{\circ}\text{C}$ during the gradual addition.

27. A method as claimed in claim 25 or 26, wherein the pH is substantially maintained at between 3 and 6 during the gradual addition.

28. A method as claimed in claim 25, 26 or 27, wherein after the gradual addition, the reaction mixture is acidified and/or heated to $\geq 25^{\circ}\text{C}$.

29. A method of making a dye composition as defined in any one of claims 3 to 5 or 8 to 11 as dependent on claim 3, 4 or 5, the method comprising the steps of:

(a) making an α -form of the dye (III) or of a salt of the dye as defined in the method of any one of claims 22 to 28, and

(b) mixing said α -form of dye (III) or salt thereof with one or more dyes including dye (II) or a salt thereof as defined in claim 1.

INTERNATIONAL SEARCH REPORT

International Application No
PCT/GB 00/00119

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C09B67/22 D06P3/42 C09B29/045

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C09B D06P

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	EP 0 347 685 A (BAYER AG) 27 December 1989 (1989-12-27) abstract page 13, line 11 - line 13; example 8	1-21, 29
Y	GB 1 112 146 A (BASF) cited in the application page 10, line 34; claim 5; example 1	1-29
Y	GB 1 394 367 A (ICI LTD) 14 May 1975 (1975-05-14) cited in the application example 1	1-21, 29
Y	GB 2 030 163 A (BASF AG) 2 April 1980 (1980-04-02) page 1, line 29 - line 40; examples	22-28
	-/-	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

12 April 2000

Date of mailing of the international search report

26/04/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Dauksch, H

INTERNATIONAL SEARCH REPORT

International Application No.

PCT/GB 00/00119

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

[illegible]

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/GB 00/00119

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0347685 A	27-12-1989	DE 3821338 A DE 58908673 D JP 1932372 C JP 2020568 A JP 6062878 B US 5160348 A	28-12-1989 12-01-1995 26-05-1995 24-01-1990 17-08-1994 03-11-1992
GB 1112146 A		BE 682396 A CH 468443 A DE 1544375 A FR 1482764 A NL 6608032 A US 3455898 A	12-12-1966 11-12-1969 04-09-1967 12-12-1966 15-07-1969
GB 1394367 A	14-05-1975	US 4211696 A	08-07-1980
GB 2030163 A	02-04-1980	DE 2831675 A	07-02-1980
JP 10140029 A	26-05-1998	NONE	
FR 2203855 A	17-05-1974	DE 2251706 A CH 584278 A GB 1438586 A IT 997892 B JP 1193718 C JP 49097014 A JP 58024461 B	25-04-1974 31-01-1977 09-06-1976 30-12-1975 12-03-1984 13-09-1974 21-05-1983
US 3995994 A	07-12-1976	GB 1489239 A BE 831777 A BR 7504878 A CA 1045311 A CH 583807 A, B CH 583817 A DE 2533725 A ES 439871 A FR 2280742 A IT 1054643 B JP 51040488 A NL 7509071 A	19-10-1977 26-01-1976 13-07-1976 02-01-1979 14-01-1977 14-01-1977 19-02-1976 01-03-1977 27-02-1976 30-11-1981 05-04-1976 03-02-1976

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ ~~FADED~~ TEXT OR DRAWING
- ☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☒ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☒ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.